

Terry Polishing Cloth

Our full terry hand towels are made with 100% cotton 16 single open-end yarn. They pack 1LB more cotton into the pile than regular hand towels for super absorbency and thickness. These towels have no cam/dobby border so are less likely to scratch painted surfaces. They are ideal for drying large areas quickly or applying polish for a sparkling finish. This towel is a best-seller amongst automotive suppliers.



Details

Part Number	Description	Packing (DOZ)	UOM	Quantity Per Pallet	Weight Per Pallet
N030-HG1627-4	16 X 27 4 LB 100% COTTON HUNTER GREEN	10	DOZ	20	980
N030-N1627-4	16 X 27 4 LB 100% COTTON NAVY	10	DOZ	20	980
N030-R1627-4	16 X 27 4 LB 100% COTTON RED	10	DOZ	20	980
N030-W1627-4	16 X 27 4 LB 100% COTTON WHITE	10	DOZ	20	980

Technical Specifications

Pass Acceptable Fail


Size Tolerance

W 2%, L -5%




Weight Tolerance


+6%



Dimensional Stability to Washing L -8%




Dimensional Stability to Washing W -1%




Breaking Strength length

175 N




Breaking Strength width

135 N



Color Shade

4




Color Fastness to Light

3-4




Color Shade Variation after 5 washes

4




Differential Shrinkage (After 5 Washes)

0.18"



Skew

3.5%




Dry Crocking

4-5



Wet Crocking

4



Lint

(After 5 Laundering Cycle)



Average Lint 0.90%
Terry Polishing Cloths
0.07%

Absorbency

65%



The standards that we are measured by are globally-recognized.
The standards that we hold ourselves to are higher.

Size & Weight Tolerance

Since cotton towels are natural woven products, there will be a variation in size and weight when coming off the loom. We use QIMA to measure our towels against industry-standard tolerance levels.

Dimensional Stability to Washing

The GB/T- 8630-2013 standard This standard was developed by the China National Textile and Apparel Council. It specifies a method to determine the dimensional change of textiles after washing and drying. This standard is applicable to textile fabrics, clothing, and other textile products and measures shrinkage after five washes.

Absorption

GB/T 22799-2009 tests the absorbency water into a fabric. GB/T 22799-2009 also tests the initial absorption speed of a fabric. Speed and weight work together to produce a deeper understanding of the fabric's ability to absorb. To pass Absorption Speed a 5"x5" square of fabric must be completely saturated in under five seconds. Total Absorbency is the amount of water absorbed into the fabric at the end of that five seconds.

Buyer beware! Many manufacturers use fabric softener to make their towels seem softer. This reduces the absorbency rate of a towel. Water beads on the surface as the softener clogs the fabric with an impermeable chemical.

Color Shade Standard AATCC

The color change scale consists of nine pairs of grey colored chips, from grades 1 to 5 (with four half steps). Specimens of a given hue match against grey chips. They equate differences in lightness with differences in color. One sample is a control, the other is washed. Grade 5 represents no change, and grade 1 depicts a severe change in some standards.

Color Fastness to Rubbing – “Dry Crocking”

Dry Crocking is done using AATCC[®] Crock Meter that rubs a dry piece of sample against a white fabric for a specific time. Then the white piece of fabric was measured against AATCC[®] Grayscale for staining to see how much color was migrated.

Color Fastness to Washing – “Wet Crocking”

Dry Crocking is done using AATCC[®] Crock Meter that rubs a wet piece of sample against a white fabric for a specific time. Then the white piece of fabric was measured against AATCC[®] Grayscale for staining to see how much color was migrated.

Breaking Strength

Fabric breaking strength is also can be called tensile strength, which refers to as the maximum tensile force when the specimen is stretched to break. It is one of the main standards to assess the intrinsic quality of textiles. The unit of fabric breaking strength is “Newton (N)” and it is used to evaluate the capability of the fabric to resist to tensile damage. Microfiber is tested two ways: Machine Direction (MD) is the length of the microfiber roll. Cross Direction is the defined width of the fabric (typically much shorter).

Elongation

Microfiber fabric is stretchable. Elongation is how much you can stretch it without breaking or tearing the fabric against the original size.

The stretched portion of the fabric is converted into a percentage, with 50% being the minimum. Microfiber is tested two ways: Machine Direction (MD) is the length of the microfiber roll. Cross Direction is the defined width of the fabric (typically much shorter).



Q I M A[®]

QC Tailored for the Textiles Industry

Modern textile manufacturers employ progressively more sophisticated methods and use a variety of natural, man-made, and synthetic fibers. The quality and durability of fabrics are directly affected by the quality of fibers, correct choice of dyes and colorants, and the use of appropriate manufacturing processes. QIMA offers inspections and laboratory tests for all modern textiles.



AATCC—the American Association of Textile Chemists and Colorists—provides test method development, quality control materials, educational development, and networking for textile and apparel professionals throughout the world.

AATCC[®]: AATCC Gray Scale for Color Change

AATCC[®]: AATCC Gray Scale for Staining

AATCC[®]: AATCC - 9 Step Chromatic Transference Scale

20 AATCC AFU: After 20 Fading (Hours) Units



Guobiao Chinese National Standards

GB/T standards are the China national standards, also called as Guobiao Standards. China GB/T standards are classified as two stages, Mandatory or Recommended. Mandatory standards have the force of law as do other technical regulations in China. They are enforced by laws and administrative regulations and concern the protection of human health, personal property and safety.