


# Brushed Microfiber Sheets

Our white microfiber sheets are made from a soft, lightweight polyester fabric that is highly durable. This breathable fabric is wrinkle-resistant, quick-drying, and repels allergens and odors. With proper care, these sheets will stay brilliantly white and fresh for an extended period. Not only are they comfortable, but they are also made to last, thanks to the durable microfiber fabric. Stock up on these sheets to save on laundry time while ensuring that you always have a fresh set of sheets on hand.

Our white microfiber sheets feature colored hems and labels for easy identification.



## Details


Part Number	Description	Thread Color	Packing	Case Dimensions (inches)	Case Weight	UPC
MFP-2030	20x30 Standard Pillowcases	N/A	6 BAGS OF 12	17 x 12 x 10	17 lbs	764950-21755-9
MFP-2040	20x40 King Pillowcases	N/A	6 BAGS OF 12	17 x 12 x 11	22 lbs	764950-21756-6
MFS-66104	66x104 Twin Flat Sheets	Black	4 PACKS OF 6	18 x 14.5 x 13	28 lbs	764950-21746-7
MFS-81108	81x108 Full Flat Sheets	Red	4 PACKS OF 6	22 x 16 x 12	35 lbs	764950-21747-4
MFS-90110	90x110 Queen Flat Sheets	Blue	4 PACKS OF 6	23 x 16 x 12	38.5 lbs	764950-21748-1
MFS-108110	108x110 King Flat Sheets	Green	4 PACKS OF 6	23 x 16 x 13.5	45.5 lbs	764950-21749-8
MFS-368012	36x80x12 Twin Fitted Sheets	Black	4 PACKS OF 6	19.5 x 13 x 13	21 lbs	764950-21750-4
MFS-398012	39x80x12 Twin XL Fitted Sheets	Orange	4 PACKS OF 6	22 x 14 x 12	22 lbs	764950-21751-1
MFS-548012	54x80x12 Full Fitted Sheets	Red	4 PACKS OF 6	22.5 x 14.5 x 12	28 lbs	764950-21752-8
MFS-608012	60x80x12 Queen Fitted Sheets	Blue	4 PACKS OF 6	20.5 x 16 x 14	32 lbs	764950-21753-5
MFS-788012	78x80x12 King Fitted Sheets	Green	4 PACKS OF 6	22 x 16 x 16	40 lbs	764950-21754-2

## Technical Specifications

Pass Acceptable Fail


### Size Tolerance

+/- 1%




### Weight Tolerance

+/- 2%




### Dimensional Stability to Washing - MD

Stable




### Breaking Strength

length 200 N




### Breaking Strength

width 270N



### Color Fastness to Rubbing

5




### Color Fastness to Washing

5



### Presence of chemicals

<= 20mg/kg ND



The standards that we are measured by are globally-recognized.  
The standards that we hold ourselves to are higher.

#### Size & Weight Tolerance

Since microfiber cloths are woven products, there will be a variation in size and weight when coming off the loom. We use QIMA to measure our towels against industry-standard tolerance levels.

#### Dimensional Stability to Washing

The GB/T- 8630-2013 standard This standard was developed by the China National Textile and Apparel Council. It specifies a method to determine the dimensional change of textiles after washing and drying. This standard is applicable to textile fabrics, clothing, and other textile products and measures shrinkage after five washes.

#### Absorption

GB/T 22799-2009 tests the absorbency water into a fabric. GB/T 22799-2009 also tests the initial absorption speed of a fabric. Speed and weight work together to produce a deeper understanding of the fabric's ability to absorb. To pass Absorption Speed a 5"x5" square of fabric must be completely saturated in under five seconds. Total Absorbency is the amount of water absorbed into the fabric at the end of that five seconds.

Buyer beware! Many manufacturers use fabric softener to make their towels seem softer. This reduces the absorbency rate of a towel. Water beads on the surface as the softener clogs the fabric with an impermeable chemical.

#### Color Shade Standard AATCC

The color change scale consists of nine pairs of grey colored chips, from grades 1 to 5 (with four half steps). Specimens of a given hue match against grey chips. They equate differences in lightness with differences in color. One sample is a control, the other is washed. Grade 5 represents no change, and grade 1 depicts a severe change in some standards.

#### Color Fastness to Rubbing – “Dry Crocking”

Dry Crocking is done using AATCC<sup>D</sup> Crock Meter that rubs a dry piece of sample against a white fabric for a specific time. Then the white piece of fabric was measured against AATCC<sup>C</sup> Grayscale for staining to see how much color was migrated.

#### Color Fastness to Washing – “Wet Crocking”

Dry Crocking is done using AATCC<sup>D</sup> Crock Meter that rubs a wet piece of sample against a white fabric for a specific time. Then the white piece of fabric was measured against AATCC<sup>C</sup> Grayscale for staining to see how much color was migrated.

#### Breaking Strength

Fabric breaking strength is also can be called tensile strength, which refers to as the maximum tensile force when the specimen is stretched to break. It is one of the main standards to assess the intrinsic quality of textiles. The unit of fabric breaking strength is “Newton (N)” and it is used to evaluate the capability of the fabric to resist to tensile damage. Microfiber is tested two ways: Machine Direction (MD) is the length of the microfiber roll. Cross Direction is the defined width of the fabric (typically much shorter).

#### Elongation

Microfiber fabric is stretchable. Elongation is how much you can stretch it without breaking or tearing the fabric against the original size. The stretched portion of the fabric is converted into a percentage, with 50% being the minimum. Microfiber is tested two ways: Machine Direction (MD) is the length of the microfiber roll. Cross Direction is the defined width of the fabric (typically much shorter).



# QIMA®

#### QC Tailored for the Textiles Industry

Modern textile manufacturers employ progressively more sophisticated methods and use a variety of natural, man-made, and synthetic fibers. The quality and durability of fabrics are directly affected by the quality of fibers, correct choice of dyes and colorants, and the use of appropriate manufacturing processes. QIMA offers inspections and laboratory tests for all modern textiles.



**AATCC—the American Association of Textile Chemists and Colorists**—provides test method development, quality control materials, educational development, and networking for textile and apparel professionals throughout the world.

AATCC<sup>B</sup>: AATCC Gray Scale for Color Change

AATCC<sup>C</sup>: AATCC Gray Scale for Staining

AATCC<sup>D</sup>: AATCC - 9 Step Chromatic Transference Scale

20 AATCC AFU: After 20 Fading (Hours) Units



#### GuoBiao Chinese National Standards

GB/T standards are the China national standards, also called as Guobiao Standards, China GB/T standards are classified as two stages, Mandatory or Recommended. Mandatory standards have the force of law as do other technical regulations in China. They are enforced by laws and administrative regulations and concern the protection of human health, personal property and safety.